



KATILAC COATINGS INC.

DIAMOND™

Extended Pot-Life Conversion Varnish

Unmatched ease of application coupled with up to 24 hours pot-life



DIAMOND™

Extended Pot-Life Conversion Varnish



The KD / R-KD Series DIAMOND™ is a line of solvent borne, two component, ultra-low HAPs, alkyd / amino resin based conversion varnishes. They are clear, yellowing resistant topcoats that feature fast dry and easy sanding along with outstanding chemical, moisture & abrasion resistance. The DIAMOND™ Series topcoats can be used in a self-sealing system or in conjunction with KCI post-catalyzed, vinyl modified, clear sanding sealers VS4 QUICKSEAL™ or VS10 QUICKSEAL PLUS™.

KD / R-KD Series DIAMOND™ Conversion Varnishes are extended pot-life products that have full functionality up to 24 hours after catalyzation.

Features

- Low odour / ultra-low formaldehyde / ultra-low HAPs / isocyanate free
- Water white; yellowing resistant
- Up to 24 hours pot-life after catalyzation
- Self-sealing or with VS4 QUICKSEAL™ or VS10 QUICKSEAL PLUS™

KD DIAMOND™

Conversion Varnish

- 42% weight solids; 36% volume solids
- 10% catalyst by volume
- 5-10% reducer by volume

R-KD DIAMOND™

Ready to Spray Conversion Varnish

- 34% weight solids; 26% volume solids
- 10% catalyst by volume
- No reducer required / ready to spray

Performance Testing

AWMAC / AWI (NAAWS Performance Standards Testing)

System #5: Conversion Varnish (Clear)

Standard score - 129/135

KD Series score - 131/135

R-KD Series score - 131/135

Flammability Testing (ASTM E 84- 08a) Surface Burn Rating

Flame Spread Index 5.0 Class 1 / Class A

Smoke Development 5.0 Class 1 / Class A

* Testing performed on concrete board by accredited independent laboratory

Hot Print Resistance (ASTM D 2091-96)

72F (18 hrs) 4 psi PASS

120F (1 hr) 4 psi PASS

140F (1 hr) 4 psi PASS

Hot/Cold Cycle Test (ASTM D 1211-97)

10 cycles PASS

* All testing results are the same for both systems unless otherwise stated

Canadian Kitchen Cabinet Association Construction & Material Testing Standards (2017) 6.2 Chemical Resistance

Orange Juice	Pass
Lemon Juice	Pass
Grape Juice	Pass
Vinegar	Pass
Ketchup	Pass
Coffee	Pass
Olive Oil	Pass
Detergent Solution	Pass
Mustard	Pass



KATILAC COATINGS INC.

Katilac Coatings Inc.

391 Hanlan Road, Unit 1
Woodbridge, ON
t. 905 856 6464 | f. 905 856 6584
info@katilaccoatings.com

Katilac Coatings Inc.

840 Appleby Line
Burlington, ON
t. 905 637 2931 | f. 905 637 8918
orders@katilaccoatings.com